

Test Report

No. SHSL1506145641TX

Date: Jul 9, 2015

Page 1 of 2

BETA TEXTILES CO., LTD
SUITE 618, HUAFANG INTERNATIONAL PLAZA, NO.178, CHENGBEI ROAD, ZHANGJIAGANG, JIANGSU

The Following sample(s) was/were submitted and identified by the client as

Sample Description : Knitted fabric: 80% cooling nylon 20% spandex HY132199 in lime light

Test Performed : Selected test(s) as requested by applicant

* * * * *

Sample Receiving Date : JUN. 26, 2015

Testing Period : JUN. 26, 2015 – JUL. 09, 2015


Test Result(s) : For further details, please refer to the following page(s).

Signed for and on behalf of
SGS-CSTC Standards Technical Services (Shanghai) Co. Ltd.

Seven Zhang
Account Executive

SGS-CSTC Standards Technical Services (Shanghai) Co. Ltd. Building No. 889 Yishan Road, Xuhui District, Shanghai, China 200038. T: (86-21) 61402888 F: (86-21) 61402886 www.sgscstc.com.cn

Member of the SGS Group (SGS SA)



Test Report

No. SHSL1506145641TX

Date: Jul 9, 2015

Page 2 of 2

Test Result

Coolness Test (q-Max)*

Test Condition:

Machine: KES—F7(THERMO LABO II)

Temperature: 20℃

Relative Humidity: 65%±4%RH


ΔT = 20℃

Back side

	1	2	3	4	5	Average
W/cm ²	0.329	0.332	0.335	0.336	0.336	0.334

* This test was carried out by external laboratory assessed as competent.

End of Report



SGS SINGAPORE PTE. LTD. 110, North Bridge Road, Singapore 079311. Tel: (65) 6349 0330. Fax: (65) 6349 0331. www.sgs.com.sg

SGS CHINA (SHANGHAI) PTE. LTD. Building No. 889, Yishan Road, Xuhui District, Shanghai, China. 200038. Tel: (86-21) 61402888. Fax: (86-21) 61402889. www.sgschina.com.cn

SGS CHINA (SHANGHAI) PTE. LTD. Building No. 889, Yishan Road, Xuhui District, Shanghai, China. 200038. Tel: (86-21) 61402888. Fax: (86-21) 61402889. www.sgschina.com.cn

Member of the SGS Group (SGS SA)