

# Test Report

No. SHSL1506145628TX

Date: Jul 9, 2015

Page 1 of 2

BETA TEXTILES CO., LTD  
SUITE 618, HUAFANG INTERNATIONAL PLAZA, NO.178, CHENGBEI ROAD, ZHANGJIAGANG, JIANGSU

The Following sample(s) was/were submitted and identified by the client as

Sample Description : Knitted fabric: 94% cooling nylon 6% spandex HY132278 in black

Test Performed : Selected test(s) as requested by applicant

\* \* \* \* \*


Sample Receiving Date : JUN. 26, 2015

Testing Period : JUN. 26, 2015 – JUL. 09, 2015

Test Result(s) : For further details, please refer to the following page(s).


Signed for and on behalf of  
SGS-CSTC Standards Technical Services (Shanghai) Co. Ltd.

Seven Zhang  
Account Executive



SGS-CSTC Standards Technical Services (Shanghai) Co. Ltd.  
 Building No. 889 Yishan Road, Xuhui District, Shanghai, China 200038  
 Tel: (86-21) 61402888 Fax: (86-21) 61402886  
 www.sgstechnical.com.cn  
 E-mail: china@sgs.com

Member of the SGS Group (SGS SA)



# Test Report

No. SHSL1506145628TX

Date: Jul 9, 2015

Page 2 of 2

## Test Result

### Coolness Test (q-Max)\*

Test Condition:

Machine: KES—F7(THERMO LABO II)

Temperature: 20℃

Relative Humidity: 65%±4%RH


ΔT = 20℃

### Back side

	1	2	3	4	5	Average
W/cm <sup>2</sup>	0.236	0.233	0.239	0.234	0.240	0.236

\* This test was carried out by external laboratory assessed as competent.

\*\*\*End of Report\*\*\*



SGS (Shanghai) Testing Certification Co., Ltd. Building No. 889 Yishan Road, Xuhui District, Shanghai, China. 200033. T: (86-21) 61402888 F: (86-21) 61402886 www.sgschina.com.cn

SGS (Shanghai) Testing Certification Co., Ltd. Building No. 889 Yishan Road, Xuhui District, Shanghai, China. 200033. T: (86-21) 61402888 F: (86-21) 61402886 www.sgschina.com.cn

Member of the SGS Group (SGS SA)